
ALPOLIC™A1

Aluminium composite panels Technical data

WORLD FIRST: Fire protection class A1

ALPOLIC™ A1 aluminium composite panels are classified according to the European fire protection standard DIN EN 13501-1 for building material for fire protection class A1 ("Euroclass A1"). ALPOLIC™ is the world's first aluminium composite material (ACM) with A1 Fire classification. This means that the product is non-combustible and does not produce any smoke in the event of fire. It therefore offers an ideal sustainable alternative to façade materials made of metal or other cladding materials used for ventilated rainscreen cladding facades systems.



ALPOLICTM A1 is manufactured from two 0.5 mm thick aluminium cover sheets. These are applied to the non-combustible mineral core (3.0 mm) in a special fusing process. The particularly durable fluoropolymer resin coating LUMIFLON™ is applied to one side of the cover sheets in a coil coating process using latest coil coating technology.

Product features

- Excellent flatness
- High rigidity
- Low weight
- Robust and durable
- Impact and fracture resistant
- · Corrosion, weather, UV-resistant
- Easy to process
- Fire protection class A1 (non-combustible)
- High-quality surface coating with LUMIFLON™
- Consistent colour quality and consistency
- · Wide variety of colours and designs
- Almost 100% recyclable

Areas of application

As non-combustible aluminium composite panel with A1 classification according to EN 13501-1, ALPOLIC™ A1 is particularly suitable for areas where very high fire protection or the use of non-combustible façade materials is required for example on high-rise buildings or high-risk buildings, fire exit stair cases and the like. In addition, ALPOLIC™ A1's excellent product and processing properties as well as its wide range of choice of finishes guarantee almost unlimited architectural design possibilities – both in refurbishment and new buildings.

- Ventilated rainscreen cladding facade constructions
- Façade and roof cladding
- Veneers
- Corporate Identity
- · Interior architecture

Surface coating



The front side of the ALPOLIC™ aluminium composite panels is coated with LUMIFLON™. It is considered to be one of the world's highest quality coating based on a transparent

fluoropolymer resin (FEVE). It ensures a high colour fastness, protects reliably against weather influences, UV irradiation, corrosion, acidity and colour bleaching. The integrated antigraffiti protection makes it easy to wipe off paint smears. The coating is guaranteed for up to 20 years. The reverse side of the composite panels is provided with a polyester-based coating to protect against corrosion. Further technical details on LUMIFLON™ can be found in the corresponding data sheet, which you can download from the website: www.alpolic.eu

Colours and surfaces

The range comprises more than 200 colours and surface designs in various degrees of gloss (15 - 80%): solid colours,

metallic, sparkling, prismatic and pattern finishes. The complete range can be found on our website. where you can order samples and download color charts and technical information.



Liability/Copyright: The content of this datasheet may be changed without prior notice. No liability for the content. Technical changes and errors excepted. No data or information contained in this datasheet may be reproduced without prior written consent. ©2021 Mitsubishi Chemical Corporation. All rights reserved. ALPOLICI** is a trademarkt of MITSUBISHI CHEMICAL CORPORATION.

ALPOLIC™ | Technical Datasheet ALPOLIC™ A1 | EN | 09/2021

Specifications

Dimensions	Standard	Unit	V alue	
Total Thickness	-	mm	4 (± 0.2 mm)	
Cover sheet thickness	-	mm	0.5	
Core thickness	-	mm	3	
Width	_	mm	1,270/1,575 (± 2 mm)	
Length	-	mm	1,800 – 7,200 (± 1 mm/m)	
Bow tolerance	-	mm	max. 0.5% (5 mm/m) of the length or width	
Squareness tolerance	- mm		max. 5	
Technological Value				
Weight	-	kg/m²	8.6	
Specific gravity	-		2.15	
Tensile strength	ASTM E8	N/mm²	48.2	
0.2% proof stress	ASTM E8	N/mm²	46.5	
Elongation	ASTM E8	%	2.7	
Flexural elasticity, E	ASTM D7250	kN/mm²	mm² 45.6	
Deflection temperature	ISO 75-2	°C	115	
Thermal expansion	ASTM D696	10 ⁻⁶ /°C	20.6	
Thermal Conductivity	Calculated Value	W/m-K 0.4		
Acoustical Properties				
Sound Transmission Loss	ASTM E413	STC	27	
Surfaces				
Coil-Coating Lacquering	-	-	LUMIFLON™ (FEVE) – based fluoropolymer coating	
Aluminium alloy	_	_	3105 H44 and 3005 H44	
Gloss (measured at 60°)	ASTM D523	%	15-80	
Pencil hardness	ASTM D3363	-	Н	

International fire classifications

Country	Test Standard	Results & Classification	Remarks
EU	EN 13501-1 (below tests as required)	Reaction to fire classification: A1	
	EN ISO 1182	Passed	Core test
	EN ISO 1716 Passed		Heat potential value
	EN 13823 Passed		Panel test
Australia	AS 1530.1	Passed	Core test
	AS 1530.3	Ignitability Index 0, Spread of Flame Index 0, Heat Evolved Index 0, Smoke Developed Index 0	Panel test
Singapore	BS 476 Part 4	Passed	Core test

Core material combustibility comparison

	ALPOLIC™/fr	ALPOLIC™ A2	ALPOLIC™ A1
Portion of combustible ingredients within the core material	≼30%	≤10%	≼5%
Heat potential of the core material	≤14MJ/kg	≼3MJ/kg	≼1MJ/kg

Further certifications and approvals in planning.

ALPOLIC™ – the world's first address for aluminium composite panels

ALPOLIC™ is a brand of Mitsubishi Chemicals Corporation. For more than 50 years, planners, architects, builders and processors worldwide have been relying on our high-quality products for the building façade. BE.SAFE. is the claim that ALPOLIC™ not only holds as a product, but holistically as a corporate philosophy. This is backed by tangible arguments for more quality and safety for the building façade - from fire protection to sustainability.





Recycling

Our materials are almost 100% recyclable. Even waste from ALPOLIC™ plants is recycled.



Trademark of AGC Chemicals, LUMIFLON™ Asahi Glass Co., Ltd.



